



120 Valley Court
 Oak Ridge, TN 37830
 Ph: 865-482-5717
 FAX: 865-482-1281
 zypcoatings.com

Type YK

Highest Purity Yttrium Oxide (Y₂O₃) Coating

Type YK is a relatively-soft, low-viscosity, non-aqueous-based washcoat-type of Yttrium Oxide (Y₂O₃) coating that provides very high purity (99.99% pure) Y₂O₃ which is usable in vacuum and inert atmospheres to 2000 C (3632 F). This coating should NOT be used in air atmospheres (use Y-Aerosol there). Type YK gives **minimal outgassing**, complete by 350 C (662C)

Key Attributes

- Provides, in a solvent-based paint, the great properties of Y₂O₃ – low electrical conductivity; low thermal conductivity; superior high-temperature thermodynamic stability with molten metals, glasses, slags, and salts; inert barrier for reactions, diffusion bonding, brazing etc.
- Applies like house paints
- Completely outgassed at low temperature -- ideal for mold coating

Ideal Use

- Graphite crucibles and molds
- Anti-stick with diffusion bonding
- Superplastic forming lubricant

Use Notes

1. Resuspend if needed. Can dilute with Ethanol or with YK Binder/Thinner needed.
2. Clean surfaces to be painted of any oils dirt, scale, etc.
3. Apply 1-3 layers by brush or spray like ordinary house paint, drying after each layer
4. Allow to dry thoroughly at room temperature before use.

Safety Information

- Consult MSDS before use.
- Avoid breathing of spray/vapors.
- For Industrial Use only.



Specifications

Active Ingredient	Y ₂ O ₃
Max Use Temperature	Inert, Vac (no C) 3632 F / 2000 C Vac (with C present) 2732 F / 1500 C Air = NOT RECOMMENDED
Use Atmosphere	Vacuum or Inert
Fired Composition	>99% Y ₂ O ₃
Liquid Carrier	Ethanol/Ethyl Acetoacetate
Binder Phase	Cellulosic
Brookfield Viscosity (cps)	80-220 @2/60
Specific Gravity	1.4
Color	White
Shelf Life (months)	>12
Coverage (ft ² /gal)	100 to 400
H F R Ratings	1-2-0
Substrate Use	All

Sizes and colors

Type YK is a white colored paint.

Standard Size: 1-gallon wide-mouth Nalgene container

CAUTION: DO NOT CONTACT WET COATINGS WITH MOLTEN METAL.

ZYP Coatings, Inc. (ZYP) makes no warranties, express or implied, including the warranty of merchantability or fitness for a particular service. Product is for industrial/commercial use only. Users should determine suitability for their use. In no event will ZYP be liable for any direct, indirect, incidental, special or consequential damages or losses including, but not limited to loss of profits, in any way related to this product regardless of the legal theory asserted.